


# Technical data sheet

## BauderTEC KSD FBS

### Roofing membrane



21/08/2023

<b>Product description</b>	Elastomer bitumen air & vapour control layer, self-adhesive membrane. The lap of the membrane is equipped with a glass fleece to the underside. This allows the membrane to be sealed with either a gas torch or hot air welder.		
<b>Application fields</b>	Air & Vapour Control Layer for use in a warm roof flat roofing system.		
<b>Surface</b>	top:	mica	
	bottom:	release film (cold self-adhesive bitumen underside)	
<b>Reinforcement type and weight</b>	aluminium-polyester-combination with glass woven 200 g/m <sup>2</sup>		
<b>Article number</b>	1628 0000		

Characteristic	Test method	Unit	Value
Length	EN 1848-1	m	10
Width	EN 1848-1	m	1.08
Thickness	EN 1849-1	mm	2,5
Mass per unit area	-	kg/m <sup>2</sup>	2,5
Straightness	EN 1848-1	mm/10m	<20
Reaction to fire	EN 13501-1	-	E
Watertightness	EN 1928	-	passed
Water vapour transmission	EN 1931	m	≥1500
Flexibility at low temperature top	EN 1109	°C	≤-25
Flexibility at low temperature bottom	EN 1109	°C	≤-25
Flow resistance at elevated temperature top	EN 1110	°C	≥70
Flow resistance at elevated temperature bottom	EN 1110	°C	≥70
Max. tensile force length	EN 12311-1	N/50mm	≥1000
Max. tensile force transverse	EN 12311-1	N/50mm	≥1000
Elongation at max. tensile force length	EN 12311-1	%	≥2



Notified body: MPA Stuttgart, 0672  
EN 13970

UNITED KINGDOM Bauder Ltd 70 Landseer Road, Ipswich, Suffolk IP3 0DH  
T: +44 (0)1473 257671 - E: info@bauder.co.uk  
www.bauder.co.uk

Bauder reserves the right to update this data set without prior notice and this document is uncontrolled if printed or stored. Always confirm the latest version is used for the adoption of this product, available from our website: [bauder.co.uk/technical-centre](http://bauder.co.uk/technical-centre). Intended use of this product should be verified with Bauder to ensure suitability and compliance with applicable guidance, regulations, legislations, project requirements, specifications, and installation techniques.

# Technical data sheet

## BauderTEC KSD FBS

### Roofing membrane



Characteristic	Test method	Unit	Value
Elongation at max. tensile force transverse	EN 12311-1	%	≥2
External fire performance	CEN/TS 1187	-	Product has been fire tested as part of a system assembly and this information can be obtained in the Fire Test Report available from Bauder Ltd.

<b>Installation guidance</b>	The labelled edge strip must cover the unlabelled edge strip of the previously installed membrane, and the laps must be welded utilising heat and with pressure applied using a long-handled lap roller. A 5 to 10mm bead of bitumen has to be visible to ensure the laps are sealed. Once the laps are sealed, the membrane can be used as temporary waterproofing. A temporary waterproofing is a temporary protection against rain. It is part of the concept of a temporary waterproofing, and this must be monitored during the construction phase and, inspected for damage prior to installation of the rest of the waterproofing system. If the membrane is left exposed after a maximum period of 4 months, the membrane should be covered by the additional waterproofing system. It must also be clear that the criteria of a permanent waterproofing cannot be expected from this temporary waterproofing application.
<b>Product storage guidance</b>	On end/Upright - The membranes must also be protected from UV rays, moisture and heat.
<b>Pallet size</b>	Pallet size =24 rolls/259,2m <sup>2</sup> per pallet
<b>Storage temperature range</b>	+5°C to +30°C
<b>Packaging material</b>	The product will be delivered on wooden pallets with plastic overwrap to protect the product. Each roll has a paper wrapping/tape to the external of the product, which must be removed before use.
<b>Handling/PPE</b>	All persons using the product should be fully aware of the manual handling methods as roofing materials are heavy and can cause serious injury. When using/handling the product, installers should be provided with, and wear, suitable personal protective equipment.
<b>Shelf life</b>	When stored correctly, the product has a stated shelf life of 9 months. We would suggest additional installation techniques may be required to ensure adequate adhesion is achieved.
<b>Disposal guidance</b>	Bitumen waste can be disposed of with household waste or commercial waste similar to household waste (European waste catalogue EWC number 170302 "asphalt tar-free").
<b>Re-use options of product</b>	Please refer to EPD stated below in Certification and environmental information.
<b>Further information/documents</b>	Current documents such as DoC's, DoP's (where relevant), brochures, installation guides, etc. can be found by visiting <a href="http://www.bauder.co.uk">www.bauder.co.uk</a>
<b>Certification and environmental information</b>	<p><b>BBA Certificate No.:</b> 10/4744</p> <p><b>Environmental Product Declaration:</b> GlobalEPD-IntEPD S-P-00768</p> <p><b>International Standards Organisation (ISO):</b> ISO 9001:2015 Quality Management Certificates EN1271 (UK) and 70499/03-15_e (Germany)</p> <p>ISO 14001:2015 Environmental Management Certificates A10552 (UK) and 70499/03-15_d (Germany)</p> <p>ISO 50001: 2011 Energy Management Certificate 70499/03-15_c (Germany)</p>
<b>Safety Data Sheet</b>	Safety Data Sheets are designed to provide the necessary information to recipients of substances and mixtures in the EU & UK. This product is classed as an article; therefore, this product does not have a requirement for a Safety Data Sheet.



Notified body: MPA Stuttgart, 0672  
EN 13970