

# Technical data sheet

## BauderTHERMOPLAN T 15

### FPO Coverstrip Roofing membrane



06/06/2024

|                                      |  |                      |
|--------------------------------------|--|----------------------|
| <b>Product description</b>           | Polyester reinforced flexible polyolefin membrane (FPO), an alloy of thermoplastic and rubber.                   |                      |
| <b>Application fields</b>            | Membrane can be mechanically fastened, adhered or loose-laid ballasted. Can be used under green roof landscaping |                      |
| <b>Surface</b>                       | top:   | silver grey RAL 7001 |
|                                      | bottom:  | black                |
| <b>Reinforcement type and weight</b> | synthetic reinforced polyester   |                      |
| <b>Article number</b>                | 6615 1020  |                      |



| Characteristic                            | Test method  | Unit              | Value              |
|---|--------------|-------------------|--------------------|
| Visible defects                           | EN 1850-2    | -                 | no visible defects |
| Length                                    | EN 1848-2    | m                 | 20(-0/+5%)         |
| Width                                     | EN 1848-2    | m                 | 0,2(-0,5/+1%)      |
| Straightness                              | EN 1848-2    | mm                | < 30               |
| Flatness                                  | EN 1848-2    | mm                | < 10               |
| Mass per unit area                        | EN 1849-2    | kg/m <sup>2</sup> | 1,8(-5/+10%)       |
| Effective thickness                       | EN 1849-2    | mm                | 1,5 (-5/+10%)      |
| Water tightness                           | EN 1928 - B  | -                 | passed             |
| Reaction to fire                          | EN 13501-1   | -                 | class E            |
| Joint peel resistance                     | EN 12316-2   | N/50mm            | ≥300               |
| Joint shear resistance                    | EN 12317-2   | N/50mm            | ≥500               |
| Tensile strength ld                       | EN 12311-2 A | N/50mm            | ≥1200              |
| Tensile strength td                       | EN 12311-2 A | N/50mm            | ≥1200              |
| Elongation ld                             | EN 12311-2 A | %                 | ≥19                |
| Elongation td                             | EN 12311-2 A | %                 | ≥19                |
| Resistance to impact hard surface         | EN 12691     | mm                | ≥700               |
| Resistance to impact soft surface         | EN 12691     | mm                | ≥950               |
| Resistance to static loading hard surface | EN 12730     | kg                | ≥20                |
| Resistance to static loading soft surface | EN 12730     | kg                | ≥20                |
| Tear resistance (length)                  | EN 12310-2   | N                 | > 350              |



Notified body: MFPA Leipzig, 0800  
EN 13956 : 2012, EN 13967 : 2012

Notified body: BBA 0836  
BS EN 13956

# Technical data sheet

## BauderTHERMOPLAN T 15

### FPO Coverstrip Roofing membrane



| Characteristic  | Test method                     | Unit | Value               |
|---|---------------------------------|------|---------------------|
| Tear resistance (transversal)                         | EN 12310-2                      | N    | > 350               |
| Resistance to root penetration                        | EN 13948/FLL                    | -    | passed              |
| Dimensional stability Id                              | EN 1107-2                       | %    | ≤0,3                |
| Flexibility at low temperature                        | EN 495-5                        | °C   | ≤ -30               |
| UV exposure   | EN 1297                         | -    | passed ( > 5000 h ) |
| Durability Watertightness after artificial ageing     | EN 1296 - EN 1928 (B 24h/60kpa) | -    | passed              |
| Durability Watertightness after exposure to chemicals | EN 1847 - EN 1928 (B 24h/60kpa) | -    | passed              |
| Hail resistance hard surface                          | EN 13583                        | m/s  | NPD                 |
| Hail resistance soft surface                          | EN 13583                        | m/s  | ≥39                 |
| Water vapour transmission                             | EN 1931                         | -    | 200000 (±30%)       |
| sd-value  | EN 1931                         | m    | 300                 |
| Exposure to bitumen                                   | EN 1548                         | -    | passed              |
| Nail Shaft test                                       | EN 12310-1                      | N    | > 400               |
| External fire performance                             | CEN/TS 1187                     | -    | not applicable      |

|  |   |
|--|---|
| <b>Product storage guidance</b>                    | Store the materials outdoors, laid horizontal/flat and off the ground with suitable robust UV resistant, flame-retardant tarpaulin. Ensure the product(s) are clear of buildings and any other storage areas. Where there are storage containers on site, these may be suitable for storing products. |
| <b>Pallet size</b>                                 | Pallet size = 16 rolls/320m <sup>2</sup> per pallet   |
| <b>Packaging material</b>                          | The product will be delivered on wooden pallets with polyethylene overwrap to protect the product. Each roll has a recycled cardboard core. Recycled nylon straps contain the rolls on a pallet.  |
| <b>Handling/PPE</b>                                | All persons using the product should be fully aware of the manual handling methods as roofing materials are heavy and can cause serious injury. When using/handling the product, installers should be provided with, and wear, suitable personal protective equipment.                                |
| <b>Disposal guidance</b>                           | Waste of the product is not a hazardous substance. Observe local regulations. European Waste Catalogue EWC number 170203 "Plastic Mirror Non hazardous"   |
| <b>Re-use options of product</b>                   | Please refer to EPD stated below in Certification and environmental information.  |
| <b>Further information/documents</b>               | Current documents such as DoC's, DoP's (where relevant), brochures, installation guides, etc. can be found by visiting <a href="http://www.bauder.co.uk">www.bauder.co.uk</a>   |
| <b>Certification and environmental information</b> | <p><b>BBA Certificate No.:</b><br/>04/4120</p> <p><b>FM Approval:</b><br/>Not applicable</p> <p><b>Environmental Product Declaration:</b><br/>EPD-BAU-20130189-IBCC-DE</p> <p><b>International Standards Organisation (ISO):</b></p>  |



Notified body: MFPA Leipzig, 0800  
EN 13956 : 2012, EN 13967 : 2012

Notified body: BBA 0836  
BS EN 13956

# Technical data sheet

## BauderTHERMOPLAN T 15

### FPO Coverstrip Roofing membrane



ISO 9001:2015 Quality Management  
Certificate 70499/03-15\_e (Germany)

ISO 14001:2015 Environmental Management  
Certificate 70499/03-15\_d (Germany)

ISO 50001: 2011 Energy Management  
Certificate 70499/03-15\_c (Germany)

#### Safety Data Sheet

Safety Data Sheets are designed to provide the necessary information to recipients of substances and mixtures in the EU & UK. This product is classed as an article; therefore, this product does not have a requirement for a Safety Data Sheet.



Notified body: MFPA Leipzig, 0800  
EN 13956 : 2012, EN 13967 : 2012

Notified body: BBA 0836  
BS EN 13956