## Technical data sheet BauderTHERMOFOL D 18 PVC Detailing membrane



## 06/06/2024

Product description	Unreinfor	ced PVC-P single ply roofing membrane	-	
Application fields		iling membrane should be used around penetrations and at details ovement of the structure(s) is likely.		
Surface	top:	blue grey RAL 7031		
	bottom:	dark grey		
Reinforcement type and weight	unreinfor	ced		
Article number	6101 605	0		

Characteristic	Test method	Unit	Value
Visible defects	EN 1850-2	-	no visible defects
Length	EN 1848-2	m	10(-0/+5%)
Width	EN 1848-2	m	0,5(-0,5/+1%)
Straightness	EN 1848-2	mm	< 30
Flatness	EN 1848-2	mm	< 10
Mass per unit area	EN 1849-2	kg/m²	2,2(-5/+10%)
Effective thickness	EN 1849-2	mm	1,8(-5/+10%)
Water tightness	EN 1928 - B	-	passed
Reaction to fire	EN 13501-1	-	class E
Joint peel resistance	EN 12316-2	N/50mm	≥200
Joint shear resistance	EN 12317-2	N/50mm	≥450
Tensile strength Id	EN 12311-2 B	N/mm²	≥13
Tensile strength td	EN 12311-2 B	N/mm²	≥13
Elongation Id	EN 12311-2 B	%	≥300
Elongation td	EN 12311-2 B	%	≥300
Tear resistance (length)	EN 12310-2	Ν	> 150
Tear resistance (transversal)	EN 12310-2	Ν	> 150
Dimensional stability Id	EN 1107-2	%	≤2
Flexibility at low temperature	EN 495-5	°C	≤ -30
UV exposure	EN 1297	-	passed, class 0 ( > 5000 h )
Water vapour transmission	EN 1931	-	20000 (±30%)
sd-value	EN 1931	m	36

UNITED KINGDOM Bauder Ltd 70 Landseer Road, Ipswich, Suffolk IP3 0DH T: +44 (0)1473 257671 - E: technical@bauder.co.uk www.bauder.co.uk

Bauder reserves the right to update this data set without prior notice and this document is uncontrolled if printed or stored. Always confirm the latest version is used for the adoption of this product, available from our website: bauder.co.uk/technical-centre. Intended use of this product should be verified with Bauder to ensure suitability and compliance with applicable guidance, regulations, legislations, project requirements, specifications, and installation techniques.

## Technical data sheet BauderTHERMOFOL D 18 PVC Detailing membrane



Characteristic	Test method	Unit	Value		
External fire performance	CEN/TS 1187	-	not applicable		
Product surface finish	BauderTHERMOFOL D has a standard thickness of 1.8mm to ensure a minimum thickness of membrane for all applications.				
Product storage guidance	Store the materials outdoors, laid horizontal/flat and off the ground with suitable robust UV resistant, flame-retardant tarpaulin. Ensure the product(s) are clear of buildings and any other storage areas. Where there are storage containers on site, these may be suitable for storing products.				
Pallet size	Pallet size = 75 rolls/375m <sup>2</sup> per pallet				
Packaging material	The product will be delivered on wooden pallets with polyethylene overwrap to protect the product. Each roll has a recycled cardboard core. Recycled nylon straps contain the rolls on a pallet.				
Handling/PPE	All persons using the product should be fully aware of the manual handling methods as roofing materials are heavy and can cause serious injury. When using/handling the product, installers should be provided with, and wear, suitable personal protective equipment.				
Disposal guidance	Waste of the product is not a hazardous substance. Observe local regulations. European Waste Catalogue EWC number 170203 "Plastic Mirror Non hazardous"				
Re-use options of product	Please refer to EPD stated below in Certification and environmental information.				
Further information/documents	Current documents such as DoC's, DoP's (where relevant), brochures, installation guides, etc. can be found by visiting www.bauder.co.uk				
Certification and environmental information	BBA Certificate No.: 06/4354				
	FM Approval: Not applicable				
		Environmental Product Declaration: EPD-BAU-20130189-IBCC-DE International Standards Organisation (ISO): ISO 9001:2015 Quality Management Certificate 70499/03-15_e (Germany) ISO 14001:2015 Environmental Management Certificate 70499/03-15_d (Germany)			
	ISO 9001:201				
		011 Energy Management 199/03-15_c (Germany)			
Safety Data Sheet	Safety Data Sheets are designed to provide the necessary information to recipients of substances and mixtures in the EU & UK. This product is classed as an article; therefore, this product does not have a requirement for a Safety Data Sheet.				

UNITED KINGDOM Bauder Ltd 70 Landseer Road, Ipswich, Suffolk IP3 0DH T: +44 (0)1473 257671 - E: technical@bauder.co.uk www.bauder.co.uk